



Institut pro testování a certifikaci, a.s.
Divize CSI - Centrum stavebního inženýrství

Fire Technical Laboratory

**AUTHORIZED
BODY**

**NOTIFIED
BODY**

**CLASSIFICATION OF REACTION TO FIRE IN
ACCORDANCE WITH
ČSN EN 13501-1:2019**

Applicant: Příhoda s.r.o.
Za Radnicí 476
539 01 Hlinsko
Czech Republic

Prepared by: Institut pro testování a certifikaci, a.s.
Divize CSI – Centrum stavebního
inženýrství
Pražská 16, 102 00 Praha 10
Czech Republic

Product name: Textile product „Příhoda NMF“

**Classification
report No.:** PK-21-115

Issue number: 1/2

Date of issue: 1st July 2021

This classification report consists of 5 pages and may only be used or reproduced in its entirety.

Address:
PRAŽSKÁ 16, 102 00 PRAHA 10, Czech Republic, E mail: csias@csias.cz, <http://www.csias.cz>
Reg. No. 47910381, VAT No. CZ47910381.
Fire Technical Laboratory, E-mail: ptl@csias.cz
Phone: +420 281 017 111, Fax: +420 281 017 455

1. DETAILS OF CLASSIFIED PRODUCT

Nature and end use application:

The classification of the product *Textile product „Příhoda NMF“* is valid for the following end use application:

Hanged textile air distribution system

Description:

The composition of the product *Textile product „Příhoda NMF“* is identical to product Příhoda MHI tested on 31st July 2007. Difference is only in mass per unit area and thickness.

Parameters of tested samples:

Product sample	mass per unit area	thickness
Příhoda NHI	470 g/m ²	0,45 mm
Příhoda NMF	290 g/m ²	0,25 mm

2. TEST REPORTS AND TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION

Test reports

Name of laboratory	Name of sponsor	Test report ref. no.	Test method
CSI a.s., Fire technical laboratory	Příhoda s.r.o.	13670 – 1/2 15406 – 1/2	ČSN EN ISO 11925-2
CSI a.s., Fire technical laboratory	Příhoda s.r.o.	13670 – 2/2 15406 – 2/2 16/329/P079	ČSN EN 13823
ITC a.s. divize CSI, Fire technical laboratory	Příhoda s.r.o.	21/P318	ČSN EN 13823

Measured values and test results

Test method	Parameter	Number of test	Results		
			Continuous parameter mean (m)	Compliance parameters	
ČSN EN ISO 11925-2 exposition = 30 s surface flame attack	$F_s \leq 150 \text{ mm}^{(1)}$ ignition of filter paper ⁽¹⁾	3 3	yes no	yes (B to D) no (d0)	
	$F_s \leq 150 \text{ mm}^{(2)}$ ignition of filter paper ⁽²⁾	3 3	yes no	yes (B to D) no (d0)	
	$FIGRA_{0,2 \text{ MJ}}$ (W/s) $LFS < \text{edge}$ $THR_{600 \text{ s}}$ (MJ)	3 3 3	6,7 yes 0,3	≤ 120 (B) yes (B) $\leq 7,5$ (B)	
	$SMOGRA$ (m^2/s^2) $TSP_{600 \text{ s}}$ (m^2) flaming droplets / particles	3 3 3	16,0 53,7 no	≤ 30 (s1) ≤ 50 (s1) no (d0)	
ČSN EN 13823 sample tested on 31 st July 2007	$FIGRA_{0,2 \text{ MJ}}$ (W/s) $LFS < \text{edge}$ $THR_{600 \text{ s}}$ (MJ)	3 3 3	6,7 yes 0,3	≤ 120 (B) yes (B) $\leq 7,5$ (B)	
	$SMOGRA$ (m^2/s^2) $TSP_{600 \text{ s}}$ (m^2) flaming droplets / particles	3 3 3	16,0 53,7 no	≤ 30 (s1) ≤ 50 (s1) no (d0)	
	ČSN EN 13823 sample tested on 16 th March 2011	$FIGRA_{0,2 \text{ MJ}}$ (W/s) $LFS < \text{edge}$ $THR_{600 \text{ s}}$ (MJ)	1 1 1	3,0 yes 0,3	≤ 120 (B) yes (B) $\leq 7,5$ (B)
		$SMOGRA$ (m^2/s^2) $TSP_{600 \text{ s}}$ (m^2) flaming droplets / particles	1 1 1	7,0 37,1 no	≤ 30 (s1) ≤ 50 (s1) no (d0)
		ČSN EN 13823 sample tested on 12 th April 2016	$FIGRA_{0,2 \text{ MJ}}$ (W/s) $LFS < \text{edge}$ $THR_{600 \text{ s}}$ (MJ)	1 1 1	0 yes 0,9
$SMOGRA$ (m^2/s^2) $TSP_{600 \text{ s}}$ (m^2) flaming droplets / particles			1 1 1	0 24,9 no	≤ 30 (s1) ≤ 50 (s1) no (d0)
ČSN EN 13823 sample tested on 26 th June 2021	$FIGRA_{0,2 \text{ MJ}}$ (W/s) $LFS < \text{edge}$ $THR_{600 \text{ s}}$ (MJ)		1 1 1	0 yes 0,5	≤ 120 (B) yes (B) $\leq 7,5$ (B)
	$SMOGRA$ (m^2/s^2) $TSP_{600 \text{ s}}$ (m^2) flaming droplets / particles		1 1 1	0 29,2 no	≤ 30 (s1) ≤ 50 (s1) no (d0)

3. CLASSIFICATION AND DIRECT FIELD OF APPLICATION**Reference and direct field of application**

This classification has been carried out in accordance with the clauses 11.6, 11.9.3 and 11.10.1 of ČSN EN 13501-1:2019.

Classification

The product *Textile product „Příhoda NMF“*, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s2

The additional classification in relation to flaming droplets/particles is:

d0

The format of the reaction to fire classification for *Textile product „Přihoda NMF“* is:

Fire behaviour		Smoke production			Flaming droplets	
B	-	s	2	,	d	0

Reaction to fire classification: B-s2, d0

Field of application

This classification is valid for the following end use conditions:

- Without backing

This classification is valid for the following product parameters:

- mass per unit area: 290 to 470 g/m²
- colour: without limitation

4. LIMITATIONS

Restrictions

This classification report is valid, provided that the technical specifications of the product will not be changed.

Warning

This document does not represent type approval or certification of the product.

Prepared:



.....
Jiří Socha



Reviewed:



.....
Vít Slaboch
head of laboratory